WHAT IS CLAIMED IS:

- 1. A metal comprising:
 - a substrate with an exterior surface; and
- a protective biofilm positioned on said exterior surface that reduces corrosion of said exterior surface;

wherein said metal is not steel, copper or aluminum.

2. The metal of Claim 1, wherein said metal is brass UNS-C26000.

10

- 3. The metal of Claim 1, wherein said biofilm is a bacterium.
- 4. The metal of Claim 3, wherein said bacterium is an aerobe.
- 15 5. The metal of Claim 4, wherein said bacterium is *Bacillus subtilis* or *Bacillus licheniformis*.
 - 6. The metal of Claim 1, wherein said biofilm is between about 10 μm and about 20 μm thick.

20

- 7. A method for reducing metal corrosion comprising:
 - providing a metal with an exterior surface;
- applying on said exterior surface a protective biofilm that reduces corrosion of said exterior surface;
- wherein said metal is not copper, aluminum or steel.
 - 8. The method of Claim 7, wherein said providing step includes the step of providing a metal that is brass UNS-C26000.
- 30 9. The method of Claim 7, wherein said applying step includes the step of applying a protective biofilm that is a bacterium.

- 10. The method of Claim 9, wherein said applying step includes the step of applying a bacterium that is an aerobe.
- 11. The method of Claim 10, wherein said applying step includes the step of applying a bacterium that is *Bacillus subtilis* or *Bacillus licheniformis*.
 - 12. The method of Claim 7, wherein said applying step includes the step of applying a protective biofilm that is between about 10 μ m and about 20 μ m thick.
- 10 13. The method of Claim 7, wherein said providing step includes the step of providing a metal that is immersed in a liquid.
 - 14. The method of Claim 13, wherein said providing step includes the step of providing a metal that is immersed in artificial seawater or Luria-Bertani medium.

15

- 15. A metal comprising:
 - a substrate with an exterior surface; and
- a protective biofilm positioned on said exterior surface that reduces corrosion of said exterior surface;
- wherein said protective biofilm is a bacterium that secretes a polyanionic chemical composition.
 - 16. The metal of Claim 15, wherein said metal is selected from the group consisting of aluminum, aluminum alloy, copper, a copper alloy, titanium, a titanium alloy, nickel and a nickel alloy.
 - 17. The metal of Claim 15, wherein said metal is steel.
 - 18. The metal of Claim 17, wherein said steel is mild steel-1010.

30

25

19. The metal of Claim 15, wherein said bacterium is an aerobe.

20. The metal of Claim 19, wherein said bacterium is *E. coli*.

5

25

- 21. The metal of Claim 15, wherein said bacterium has been genetically engineered to secrete the polyanionic chemical composition.
- 22. The metal of Claim 15, wherein said polyanionic chemical composition is polyphosphate.
- 23. The metal of Claim 15, wherein said biofilm is between about 10 μm and about 20 μm thick.
- A method for reducing corrosion comprising:
 providing a metal with an exterior surface;
 applying on said exterior surface a protective biofilm that reduces corrosion of

 said exterior surface;

wherein said protective biofilm is a bacterium that secretes a polyanionic chemical composition.

- The method of Claim 24, wherein said providing step includes the step of
 providing a metal that is selected from the group consisting of aluminum, a aluminum alloy, copper, copper alloy, titanium, a titanium alloy, nickel and a nickel alloy.
 - 26. The method of Claim 24, wherein said providing step includes the step of providing a metal that is steel.
 - 27. The method of Claim 26, wherein said providing step includes the step of providing a metal that is mild steel-1010.
- 28. The method of Claim 24, wherein said applying step includes the step of applying a bacterium that is an aerobe.

- 29. The method of Claim 28, wherein said applying step includes the step of applying a bacterium that is *E. coli*.
- 30. The method of Claim 24, wherein said applying step includes the step of applying a bacterium that has been genetically engineered to secrete the polyanionic chemical composition.
 - 31. The method of Claim 24, wherein said applying step includes the step of applying a polyanionic chemical composition that is polyphosphate.
- 32. The method of Claim 24, wherein said applying step includes the step of applying a biofilm that is between about 10 μm and about 20 μm thick.

10

- 33. The method of Claim 24, wherein said providing step includes the step of providing a metal that is immersed in a liquid.
 - 34. The method of Claim 24, wherein said providing step includes the step of providing a metal that is immersed in artificial seawater or Luria-Bertani medium.

24 CA1 - 287818.1